

IN THE SPECIFICATION:

Page 10, lines 14-19:

According to the invention, said mixture can be
~~calcinated~~ calcined in two stages:

- at a temperature T_1 higher than 1225°C , for example, between
 1225 and 1275°C , for less than 5 minutes,
- then at a temperature T_2 lower than 1150°C , for example,
between 1100 and 1150°C , for at least 30 minutes.